



**Audurra™ Masking foil HDPE**

**MASKING**

**Description:**

A good cutting and static adhesive of the Audurra HDPE Masking Foil (Polythene transparent) make the working steps faster and are the conditions for a save and perfect covering. Due to its heat resistance up to 110°C it can be used with infrared dryers. Important: The vehicle should be dry before masking. No severance of water or paint.



**Available in:**

Article number	Description	Dimension
D15352435	Audurra™ Masking foil HDPE	4 m x 300 m
D15369358	Audurra™ Masking foil HDPE	5 m x 240 m

**Compatible with:**

Article number	Article description	Packaging unit
D15352436	Audurra mobile dispenser for foil cartons	1 piece
D15352432	Audurra Foil Cutter	1 bundle = 5 pieces



**Audurra™ Masking foil HDPE**

**MASKING**

**Properties:**

Property	Value & measuring unit	Measuring method
Density	0,95 g / cm <sup>3</sup>	following DIN EN 1183
Thickness	9 µm	following GPA (Thickness-profile)
Tensile Strength <i>machine direction</i>	70 N / mm <sup>2</sup>	following ASTM D 882
Tensile Strength <i>transverse direction</i>	28 N / mm <sup>2</sup>	following ASTM D 882
Elongation at break <i>machine direction</i>	422 %	following ASTM D 882
Elongation at break <i>transverse direction</i>	893 %	following ASTM D 882
Dart drop	3,45 g/µm	following ASTM 1709-91
Dimension and Design	4 m x 300 m	

**Storage remarks:**

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%.

Storage in closed rooms. Avoid exposure to UV-radiation.

This technical information has been given to the best of our knowledge. The above mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.

